



# Twin Ports Testing Inc.

1301 N. 3rd Street • Superior, WI 54880 • 715-392-7114 • Fax 715-392-7163  
218-722-1911 • 800-373-2562 • www.twinportstesting.com

Carolina Wood Pellets LLC  
6382 Georgia Road  
Franklin, NC 28734

Date Received: 9/10/2009

Date Tested: 9/10/2009

Purchase Order #:

Attn: James Wirtz II

Sample Log Number: 09C2536

Sample Designation: First Run

	MOISTURE & ASH FREE	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Moisture Total			2.49	% wt.	ASTM E871
Ash		0.34	0.33	% wt.	ASTM D1102
Sulfur		0.009	0.009	% wt.	ASTM D4239
Heating Value	8343	8315	8108	Btu/lb	ASTM E711

	MDL	MOISTURE FREE	AS RECEIVED	UNITS	METHOD
Chlorine				mg/kg	ASTM D6721

	AS RECEIVED	UNITS	AS RECEIVED	UNITS
Bulk Density		lbs/cu.ft.	Fines	% wt.
Sample Above 1.50 In		%	Durability Index	
Maximum Length		inch	Stated Bag Wt.	lbs
Diameter, Range	to	inch	Actual Bag Wt.	lbs
Diameter, Average		inch		

Prepared By: Kevin Anderson

Date: 9/14/09